Technical Data Sheet

B572 THREADLOCK Revised 03.08.10



B572 Threadlock

PRODUCT DESCRIPTION

B572 White Pipe Seal is designed for the locking and sealing of metal pipes and fittings. The product cures when confined in the absence of air between close fitting metal surfaces and prevents loosening and leakage from shock and vibration. The thixotropic nature reduces the migration of liquid product after application to the substrate. Good chemical/solvent resistance to Ethanol, Motor Oil, Unleaded Petrol and Brake Fluid. B572 is unusual in that it does not fully cure until some 60 hours after application, allowing for re-alignment of elbows and joints.

APPLICATIONS

Replaces tapes and dopes, stops gas and fluid leaks on most metals and assists in lubricating during assembly. B572 will not shred or tear which would contaminate your system. Use B572 to seal against oils, gases, chemicals, water and steam etc.

USEFUL NOTES

Wipe threads with clean shop cloth. Apply a continuous bead to 3rd or 4th thread depending on the thread length.

PROPERTIES

Instantaneous Low Pressure Seal. No locking action up to 48 hours. Easy break loose allowing re-alignment.

INSTRUCTIONS FOR USE

Ensure parts are clean, dry and free from oil and grease.

PROCEDURE FOR APPLICATION

Apply only to clean, dry parts. Degreasing directly assists results.

COMPATIBLE ACCELERATORS/PRIMERS

Non recommended.

STORAGE

Store in a cool area out of direct sunlight. Shelf Life >12 months at ambient temperature.

HEALTH & SAFETY IN USE

IRRITANT: Contains Methacrylate Esters and some products contain small amounts of Acrylic Acid. Irritates eyes, the respiratory organs and the skin. In case of contact with the skin wash immediately with plenty of water.

TECHNICAL FEATURES

Resin	Dimethacrylate
Colour	White paste
Cure speed with activator	Not recommended
Cure speed Without Activator	up to 60 hours
Viscosity Brookfield Sp3 @ 20rpm	20,000cps
Gap fill / Max threadform	0.4 mm / M36
Flash Point	>85°C
Shelf Life	36 months @ 20°C
Specific Gravity	1.25
Max Operating Temperature	-55°C to + 150°C

CURED PERFORMANCE

Full Cure Time	60 hours
Typical breakaway strength	6 N.m
Typical prevailing strength	2 N.m

PRESENTATION

B572 is available in 65ml, 50ml, 250ml and clam